


# KTU

## Description:

Testliner from waste paper.

## Printing methods:

Testliner for corrugated board.



| № | Property unit                                      | Assortment range |     |             |     |     | Test standard     |
|---|----------------------------------------------------|------------------|-----|-------------|-----|-----|-------------------|
|   |                                                    | 120              | 130 | 150         | 170 | 190 |                   |
| 1 | Tolerance, %                                       | +3/-5            |     | +4/-6       |     |     | DSTU EN ISO 536   |
| 2 | Burst strength, kPa, min                           | 260              | 290 | 340         | 360 | 380 | ISO 2759          |
| 3 | Short Span Compressive Strength SCT, CD, kN/m, min | 1,9              | 2,1 | 2,4         | 2,7 | 3,0 | ISO 9895          |
| 4 | Moisture, %                                        | 6,2-7,8          |     |             |     |     | DSTU GOST ISO 287 |
| 5 | Water Absorption Top gsm:<br>- Top<br>- Back side  |                  |     | 25-60<br>70 |     |     | DSTU EN ISO 535   |